

Flammability

1. Test Standard

1.1 Test Method

ASTM E84-17 "Standard Method of Test for Surface Burning Characteristics of Building Materials"

1.2 Sample Preparation and Conditioning

Three pieces of 8 foot long panels measuring 24 feet long, 24 inches wide and 3/4 inch thickness were placed into fire chamber with $23\pm 3^{\circ}\text{C}$ ($73\pm 5^{\circ}\text{F}$) and $50\pm 5\%$ relative humidity until day of testing. The sample was self-supporting with the face side exposed to the burner flames.

The Samples were butted end to end in the test chamber, with cement board place between the lid and sample.

1.3 Flame Spread Classification

Flame Spread	Smoke Developed	Class (NFPA, IBC)
0 through 25	Less than or equal to 450	A
26 through 75	Less than or equal to 450	B
76 through 200	Less than or equal to 450	C

※ Building Codes Cited

- **NFPA:** National Fire Protection Association "Life Safety Code" (ANSI/NFPA No. 101)
- **IBC:** International Building Code, Interior Finishes, Section 803

2. Test Result

Flame Spread: 5

Smoke Development: 130

Classification: Class A

The information contained herein is provided by Jin Gwang Industries Co., Ltd. for information purposes only and should be used by individuals with technical experience and knowledge in the area. Jin Gwang Industries Co., Ltd. does not make any representation or warranties of the usefulness or expected result of the information, and does not assume any responsibility whatsoever related to the use of the information. Exclusion of the implied warranties may not apply in certain jurisdictions.