

Color Stability Test

1. Test Method

1.1. Test Standard: NEMA LD3 2005 3.3
(Light Resistance / Color Stability)

1.2. Test Condition

- 1) Condition prior to Test: 48 hours at 23°C ± 2°C (73.4°F ± 3°F), 50% ± 5% relative humidity
- 2) Test Period: **1,000 hrs**

1.3. Classification

- 1) No Effect – No change in color or surface finish
- 2) Slight Effect – A change in color or surface finish only visible at certain angles and directions
- 3) Moderate Effect – A Change in color or surface finish visible at all angles and directions, but does not notably alter the original condition of the specimen
- 4) Severe Effect – A change in color or surface finish that markedly alters the original condition of the specimen

2. Test Result

Sample	Blister	Crazing	Color Change	Cracking	Dulling
1	No Effect	No Effect	No Effect	No Effect	No Effect
2	No Effect	No Effect	No Effect	No Effect	No Effect

The information contained herein is provided by Jin Gwang Industries Co., Ltd. for information purposes only and should be used by individuals with technical experience and knowledge in the area. Jin Gwang Industries Co., Ltd. does not make any representation or warranties of the usefulness or expected result of the information, and does not assume any responsibility whatsoever related to the use of the information. Exclusion of the implied warranties may not apply in certain jurisdictions.